

# TECHNICAL DATA SHEET

Commercial product name	<b>ECOVINYL® GB-TR-P 64 ShA</b>
Product	Transparent plasticized PVC granulate
Stabilization	Calcium / Zink
Application	Extrusion of technical profiles

Property	Test	Unit	Value
Density	PN-EN ISO 1183-3 :	g/cm <sup>3</sup>	1,20
Bulk density	PN-ISO 60: 1998/Ap1:2001	g/cm <sup>3</sup>	0,630 ÷ 0,670
Hardness according to Shore	PN-ENISO 868 :	ShA	64 ± 3
Tensile strength	PN-ISO 527-1:2012	MPa	18,17
Elongation at break		%	394

Packing	25 kg bags, 500/1200 kg big – bags
Storage	Time of storage to 12 months in closed storage rooms, moisture content of air 50 ± 30 %, ambient temperature 20 ± 10°C, on condition that material will be protected against sunlight

*Information in Technical Data Sheet is considered as accurate and reliable. However users should make their own requirements to determine suitability of product for particular application.*

