

TECHNICAL DATA SHEET

Commercial product name	ECOVINYL[®] GB-TR-P 73 ShA
Product	Transparent plasticized PVC granulate
Stabilization	Calcium / Zink
Application	Extrusion of technical profiles

Property	Test	Unit	Value
Density	PN-EN ISO 1183-3 : 2003	g/cm ³	1,21
Bulk density	PN-ISO 60: 1998/Ap1:2001	g/cm ³	0,630 ÷ 0,670
Heat stability in 200°C	PN-C-89265-4 : 1998	min	20
Hardness according to Shore	PN-ENISO 868 : 2005	ShA	73 ± 3
Tensile strength	PN-ISO 37: 2007	MPa	18,2
Elongation at break		%	376

Packing	25 kg bags, 500/1200 kg big – bags
Storage	Time of storage to 12 months in closed storage rooms, moisture content of air 50 ± 30 %, ambient temperature 20 ± 10°C, on condition that material will be protected against sunlight

This information corresponds to the current state of our knowledge and should inform about our products and their application possibilities. Therefore they are not guaranteeing certain qualities of the products for a specific application.

